

## Ageing behaviour of a silorane-based composite regarding streptococcal adhesion

Sebastian Hahnel, Martin Rosentritt, Anne Henrich, Gerhard Handel, Ralf Bürgers

**Introduction:** The aim of this *in vitro* study was to investigate the influence of artificial ageing on streptococcal adhesion to a silorane-based composite.

**Methods:** Standardized specimens (diameter 10mm, height 2mm) of a silorane-based composite (*Filtek Silorane*, 3M Espe, Seefeld, G) were prepared, and polished to high gloss using grinding paper and polishing paste. A nano-filled methacrylate-based composite was used as control (*Filtek Supreme XT*, 3M Espe). After assessment of surface roughness, specimens (n=15 for each treatment) were stored in ethanol for 7, 90 or 365 days, or thermally cycled (6000 cycles 5/55°C, 5min). Specimens were incubated either with phosphate buffered saline or natural whole saliva for 2h for pellicle formation, and subsequently with *Streptococcus mutans* suspension (2.5h, 37°C). Adherent bacteria were quantified using a fluorometric assay. Statistics: One-way ANOVA, Tukey-test ( $\alpha=.05$ ).

### Results:

Ageing protocol	<i>Filtek Silorane</i>	<i>Filtek Supreme XT</i>	<i>Filtek Silorane</i>	<i>Filtek Supreme XT</i>
	Uncoated (Mean, SD)		Saliva-coated (Mean, SD)	
<b>0 days</b>	2409.1 (1834.5)	4478.9 (2415.2)	4338.1 (2014.9)	9605.9 (2569.5)
<b>7 days</b>	608.4 (454.2)	2355.8 (1937.6)	1503.8 (1030.1)	2125.8 (1625.8)
<b>90 days</b>	1658.9 (1296.6)	3531.2 (1002.5)	1016.5 (615.6)	3655.8 (1448.7)
<b>365 days</b>	3240.1 (1432.8)	7099.1 (2726.6)	720.6 (615.9)	3777.8 (2542.7)
<b>Thermal cycling</b>	4275.4 (4093.4)	3281.6 (1711.7)	5899.1 (1878.13)	11983.6 (7924.9)

Relative fluorescence intensities showed a decrease after storage in ethanol for 7 days, indicating a decrease in streptococcal adhesion. With the exception of uncoated *Filtek Supreme XT*, thermal cycling caused a significant increase in fluorescence intensities,

suggesting higher adhesion of streptococci. Prolonged alcohol storage caused a significant increase of fluorescence intensities with the exception of saliva-coated *Filtek Silorane*.

**Conclusion:** Within the limitations of an *in vitro* study it can be concluded that ageing influences microbial adhesion to composite materials decisively. The silorane-based composite features promising results for streptococcal adhesion after artificial ageing in ethanol and thermal cycling.